

AMENDMENT NO. 1 DECEMBER 2019

TO

IS 16714 : 2018 GROUND GRANULATED BLAST FURNACE SLAG FOR USE IN CEMENT, MORTAR AND CONCRETE — SPECIFICATION

(Page 2, Table 1, Note) — Substitute the following for the existing:

‘NOTES

1 For the purpose of testing of GGBS as per IS 4032, wherever reference to cement has been made in IS 4032, it may be read as GGBS.

2 GGBS shall satisfy any one of the two requirements given at SI No. (viii) and (ix).

3 $\text{CaS} = 2.25 \times \text{Sulphide sulphur}$. Sulphide sulphur in GGBS may be estimated as per the method specified in IS 4032, assuming total sulphide sulphur exists as CaS.’